

AC-FHT2-BIO longtime ECOLABEL

Grease



High-performance extreme pressure biodegradable lithium grease.

APPLICATIONS

Biodegradable grease
ECOLABEL

Extreme pressure
Multipurpose

Recommended for severe
applications

- **AC-FHT2-BIO** is designed for on road and off road applications in environmental sensitive areas like agriculture, public works, forest, inland and coastal shipping (locks)...
- **AC-FHT2-BIO** is a multi purpose grease, especially formulated for the lubrication of bearings, slide bearings or universal joints.
- **AC-FHT2-BIO** is adapted for the lubrication of applications operating in wet, dusty and/or dry conditions and with medium load and speed in transport, agriculture and off road vehicles.
- **AC-FHT2-BIO** is developed for loss lubrication with very high environmental constraints.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system or cartridges.

SPECIFICATIONS

- ISO 6743-9: L-XCEEB 2
- DIN 51502: KP2K-30

ADVANTAGES

Extensive application
range

Durable film

Low environmental
impact : biodegradable,
low toxicity to aquatic
organisms

- Due to its multipurpose character, **AC-FHT2-BIO** may replace a wide range of greases, allowing stock rationalization and simplification of maintenance.
- Forms a durable lubrication film with a good resistance to water and variation of temperature resulting in reduction of maintenance and down-time costs.
- Miscible with most other conventional soap greases.
- **AC-FHT2-BIO** does not contain lead, or other heavy metals considered harmful to human health and the environment.
- **AC-FHT2-BIO** is an ultimately biodegradable grease, with low toxicity to aquatic organisms and contains more than 50% of renewable raw materials.

TYPICAL CHARACTERISTICS	METHODS	UNITS	AC-FHT2-BIO
Thickener		-	Lithium
NLGI Grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Brown
Appearance	Visual		Smooth
Operating temperature range		°C	- 30 to +140
Penetration at 25°C	ASTM D 217/DIN 51 818	0.1 mm	265-295
Anti-rust performance SKF- EMCOR	ISO 11007	Rating	0/0
4-ball weld load	ASTM D 2596	kgf	315
4-ball wear	ASTM D 2266	mm	0,8
Dropping point	IP 396/ISO 2176	°C	> 180
Base oil viscosity of the base oil at 40 °C	ASTM D 445/DIN 51 562-1/ISO 3104/ IP71	mm ² /s (cSt)	150
Biodegradability	OECD 301 B	%	63%

Above characteristics are mean values given as an information

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

